



浙江海利得新材料股份有限公司

地址:浙江省海宁市马桥镇

电话: (0573) 7989878 7989982

传真: (0573) 7989882

邮编: 314419

*Zhejiang Hailide New Material Co.,LTD*

Add: Maqiao town, haining city, zhejiang province

Tel: (0573) 7989982

Fax: (0573) 7989880

Postcode: 314419

<b>LAMINATED TARPAULIN 400GSM</b>			
Items / Характеристика	Data / Значение	Unit / Единица измерения	Ref.test method Стандарт измерения
Weight / вес	400gsm	Gsm / г	ISO3801:1977
Polyester Fabric / Полиэстеровая ткань	300*500/18*12	Denier/fd per inch Денье / Кол-во нитей на дюйм	DIN60001/DIN EN ISO2060
Tensile Strength	670(L)	N/ 5cm	ISO527/3:1995
Прочность на растяжение	435(W)	N/5cm	
Tearing Strength	75(L)	N/5cm	ISO4674/1:2003
Прочность на разрыв	65(W)	N/5cm	
Adhesion Strength Адгезия	70	N/5cm	DIN53357:1982

Low Temperature Морозостойкость	-30	°C	ISO13934-1:1999
Width / Ширина	3,0	meter	

Information listed above is based on our general experience and observation and is given in good faith. Halead will not accept any responsibilities with respects to factors outside of our knowledge. The values can vary according to production lot and are subject to +/-5% tolerance.